

TECHNICAL DATA SHEET



SL-341 1101 GREY LIQUID GASKET

DESCRIPTIONS:

SILOCK SL-341 1101 GREY LIQUID GASKET IS A SEMI-DRYING GRAY LIQUID GASKET THAT USES RUBBER AS THE MAIN INGREDIENTS. IT IS FORMULATED TO FORM A LAYER THICK ENOUGH TO WORK EFFICIENTLY ON UNEVEN JOINT SURFACES. IT HAS A DISTINGUISHING ABILITY TO TURN INTO RUBBER-LIKE ELASTIC SUBSTANCES WITH EXCELLENT RESISTANCE TO HEAT, OIL, GASOLINE AND PARTICULARLY LPG. IDEAL FOR THE PURPOSE OF MAKING QUALITY GASKETS IN GARAGES, WORKSHOPS, HOMES AND DO-IT-YOURSELF.

FEATURES:

- ◆ A VISCO-ELASTIC TYPE SEALANT CAPABLE OF JOINING UNEVEN SURFACES.
- ◆ EXCELLENT RESISTANCE TO HEAT, OIL, GASOLINE AND LPG.
- ◆ EASY TO APPLY AND ALLOW TO AUTOMATE THE PRODUCTION LINE WITH LABOR-SAVING EQUIPMENTS, MARKEDLY IMPROVING THE WORK EFFICIENTLY.
- ◆ HAS THE PROPERTY OF FLOWING AT ROOM TEMPERATURE.

USES:

- ◆ FOR THE PURPOSE OF MAKING QUALITY GASKETS IN GARAGES, WORKSHOPS, HOMES AND DO-IT-YOURSELF.

WE RECOMMEND PRELIMINARY COMPATIBILITY TESTS PRIOR TO APPLICATION TO ACHIEVE DESIRABLE RESULTS

APPLICATIONS:

- ◆ SURFACES MUST BE CLEAN, DRY, AND FREE FROM MOISTURE, GREASE AND OTHER STAINS BEFORE APPLICATION.
- ◆ APPLY A THIN AND UNIFORM LAYER OF LIQUID GASKET ON BOTH MATING SURFACES.
- ◆ ASSEMBLE ABOUT 1 MINUTE AFTER APPLICATION.
- ◆ APPLICATION TEMPERATURE RANGE IS FROM -40°C TO +150°C.
- ◆ SEAL TIGHTLY AFTER USE. STORE IN A COOL DRY PLACE.

SPECIFICATIONS:

APPEARANCE	GRAY HIGH VISCOSITY LIQUID
SPECIFIC GRAVITY	1.05 ± 0.05
SOLID CONTENT	46 ± 1%
VISCOSITY AT 30°C	9000 - 12000CPS
MAIN SOLVENT	HYDROCARBON SOLVENT
MAIN INGREDIENT	CHLOROPRENE RUBBER
DILUTION	TOLUENE
TEMPERATURE RANGE	40°C TO 150°C

TECHNICAL DATA SHEET



SL-341 1101 GREY LIQUID GASKET

STORAGE:

MATERIAL SHOULD BE STORED IN A DRY AND COOL PLACE BETWEEN +5°C TO +30°C.

CAUTION:

READ AND UNDERSTAND MATERIAL SAFETY DATA SHEET OF THIS PRODUCT BEFORE HANDLING OR USING.

THIS INFORMATION IS PROVIDED IN GOOD FAITH AND IS BELIEVED ACCURATE BASED ON A REVIEW OF CURRENT COMPOSITION AND INFORMATION SUPPLIED BY VENDORS. NO WARRANTY IS EXPRESSED OR IMPLIED. LIABILITY IS EXPRESSLY DISCLAIMED.

